

Section 09212

SonaSpray®"fc" Spray On Acoustical Finish

Specification Guide 10/03

PART 1 – GENERAL

1.01 Section Includes

Edit acoustical where required

- A. Sprayed cellulose insulation finish system.

1.02 Related Items

- A. Clips, hangers, supports, sleeves and other attachments to spray bases are to be placed by other trades prior to the application of sprayed insulation.
- B. Ducts, piping, conduit or other suspended equipment shall not be positioned until after the application of sprayed insulation.

1.03 Quality Assurance

- A. Manufacturer must be ISO 9001:2000 Certified.
- B. Applicator: Licensed by manufacturer.
- C. Manufacturer must subscribe to independent laboratory follow-up inspection services of Underwriters Laboratories. Each bag shall be labeled accordingly
- D. Mock-up: Apply a 100 square foot representative sample to be reviewed by the Architects and/or Owner prior to proceeding.

1.04 Submittals

- A. Copy of manufacturer's ISO 9001:2000 Certification.
- B. Submit 2 copies of test reports indicating compliance with the following:
 - 1. Minimum light reflectivity:
 - a. Arctic White: 81+
 - b. White: 73+
 - 2. NRC values per ASTM C-423 conducted by a NVLAP certified testing laboratory:

SonaSpray "fc" on Solid Backing							
Inches	125 HZ	250 HZ	500HZ	1000HZ	2000 HZ	4000 HZ	NRC
0.50"	.08	.16	.46	.87	1.07	1.12	.65
1.00"	.12	.38	.88	1.15	1.15	1.15	.90

SonaSpray "fc" on Lath/Plaster							
Inches	125 HZ	250 HZ	500HZ	1000HZ	2000 HZ	4000 HZ	NRC
0.75"	.25	.36	.74	.98	.99	.99	.75

SonaSpray "fc" on Ribbed Metal Deck							
Inches	125 HZ	250 HZ	500HZ	1000HZ	2000 HZ	4000 HZ	NRC
0.75"	.17	.58	.91	.89	.87	.84	.80

- 3. Flame Spread Index: 5 ASTM E-84/UL 723
- 4. Smoke Developed: 5 ASTM E-84/UL 723
- 5. Bond Strength
 - SonaSpray "fc" >600 psf ASTM E-736
 - SonaSpray "fc" Dura-K >900 psf ASTM E-736
- 6. Compression Strength
 - SonaSpray "fc" >400 psf ASTM E-761
 - SonaSpray "fc" Dura-K >600 psf ASTM E-761
- C. Manufacturer's written certification that product contains no asbestos, fiberglass or other man-made mineral fibers.

1.05 Delivery, Storage and Handling

- A. Deliver in original, unopened containers bearing name of manufacturer, product identification and reference to U.L. testing.
- B. Store materials dry, off ground and under cover.
- C. Protect liquid adhesive from freezing.

PART 2 – PRODUCTS

2.01 Acceptable Manufacturers

- A. International Cellulose Corporation
12315 Robin Boulevard
Houston, Texas 77045
(713) 433-6701 or (800) 444-1252
FAX: (713) 433-2029

2.02 Materials (Specify desired product)

- A. SonaSpray "fc" Acoustical Finish _____
- B. SonaSpray "fc" Dura-K _____

Color selection will affect price

- C. Color shall be as indicated in Schedule 3.05.

PART 3 – EXECUTION

3.01 Examination

- A. Examine surfaces and report unsatisfactory conditions in writing. Do not proceed until unsatisfactory conditions are corrected.
- B. Verify surfaces to receive spray insulation to determine if priming/sealing is required to ensure bonding and/or to prevent discoloration caused by migratory stains.

3.02 Preparation

- A. Provide masking, drop cloths or other satisfactory coverings for materials/surfaces that are not to receive insulation to prevent damage from over-spray.
- B. Coordinate installation of the sprayed cellulose fiber with work of other trades.
- C. Prime surfaces as required by manufacturer's instructions or as determined by examination.

3.03 Installation

- A. Average thickness to achieve NRC of 0.65 or greater.
- B. Install spray applied insulation according to manufacturer's recommendations.
- C. Cure insulation with continuous natural or mechanical ventilation.
- D. Remove and dispose of over-spray.

3.04 Protection

- A. Protect finished installation under provisions of Division 1.

3.05 Schedule

Provide a schedule when insulation requires listing by color, insulation value, NRC values and other attributes

END OF SECTION